

Valox* Resin V9230DCS

Europe-Africa-Middle East: COMMERCIAL

15% GF PEt Injection Moulding grade, Heat and Color Stabilised for dark colors only

Property

TYPICAL PROPERTIES ⁽¹⁾			
MECHANICAL	Value	Unit	Standard
Tensile Stress, yield, 5 mm/min	100	MPa	ISO 527
Tensile Stress, break, 5 mm/min	100	MPa	ISO 527
Tensile Strain, yield, 5 mm/min	2.2	%	ISO 527
Tensile Strain, break, 5 mm/min	2.2	%	ISO 527
Tensile Modulus, 1 mm/min	6200	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	160	MPa	ISO 178
Flexural Modulus, 2 mm/min	5800	MPa	ISO 178
IMPACT	Value	Unit	Standard
Izod Impact, notched 80*10*4 +23°C	5	kJ/m ²	ISO 180/1A
Izod Impact, notched 80*10*4 -30°C	5	kJ/m ²	ISO 180/1A
Charpy 23°C, V-notch Edgew 80*10*4 sp=62mm	5	kJ/m ²	ISO 179/1eA
THERMAL	Value	Unit	Standard
CTE, 23°C to 80°C, flow	3.5E-05	1/°C	ISO 11359-2
CTE, 23°C to 80°C, xflow	1.E-04	1/°C	ISO 11359-2
Vicat Softening Temp, Rate B/50	230	°C	ISO 306
Vicat Softening Temp, Rate B/120	235	°C	ISO 306
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	230	°C	ISO 75/Af
PHYSICAL	Value	Unit	Standard
Density	1.45	g/cm ³	ISO 1183
Water Absorption, (23°C/sat)	0.35	%	ISO 62
Moisture Absorption (23°C / 50% RH)	0.12	%	ISO 62
Melt Volume Rate, MVR at 265°C/1.2 kg	12	cm ³ /10 min	ISO 1133

Source GMD, last updated:04/10/2007

Processing

Parameter	Value	Unit
Injection Molding		
Drying Temperature	120 - 130	°C
Drying Time	4 - 6	hrs
Maximum Moisture Content	0.02	%
Melt Temperature	270 - 290	°C
Nozzle Temperature	260 - 280	°C
Front - Zone 3 Temperature	270 - 290	°C
Middle - Zone 2 Temperature	260 - 280	°C
Rear - Zone 1 Temperature	250 - 270	°C
Hopper Temperature	40 - 60	°C
Mold Temperature	90 - 120	°C

Source GMD, last updated:04/10/2007

THESE PROPERTY VALUES ARE NOT INTENDED FOR SPECIFICATION PURPOSES.

PLEASE CHECK WITH YOUR [\(LOCAL SALES OFFICE\)](#) FOR AVAILABILITY IN YOUR REGION

- (1) Typical values only. Variations within normal tolerances are possible for various colors. All values are measured after at least 48 hours storage at 23°C/50% relative humidity. All properties, except the melt volume and melt flow rates, are measured on injection molded samples. All samples tested under ISO test standards are prepared according to ISO 294.
- (2) Only typical data for selection purposes. Not to be used for part or tool design.
- (3) This rating is not intended to reflect hazards presented by this or any other material under actual fire conditions.
- (4) Internal measurements according to UL standards.

Disclaimer : All information, recommendation or advice given by SABIC Innovative Plastics, or any of its subsidiaries, affiliates or authorized representatives, whether written or oral, is given in good faith, to the best of its knowledge and based on current procedures in effect. Each user of the products shall convince himself, through all available sources (including finished product testing in its appropriate environment) of the suitability of the products supplied for its own particular purpose. Because actual use of the products by the user is beyond the control of SABIC Innovative Plastics Company, its subsidiaries and affiliates, such use is in the exclusive responsibility of the user. SABIC Innovative Plastics Company, its subsidiaries and affiliates cannot be held responsible respectively liable for any loss incurred through incorrect or faulty use of the products. Information, recommendations and/or advice are neither made to infringe on any patents, nor to grant a license under any patent or intellectual property right of SABIC Innovative Plastics Company or any of its subsidiaries or affiliated companies, nor to grant the right to file for any patent protection.

* Valox is a trademark of the SABIC Innovative Plastics Company

© 1997-2008 SABIC Innovative Plastics Company. All rights reserved