

LNP* Verton* Compound RX03013

Europe-Africa-Middle East:
COMMERCIAL

Also known as: PDXR03013-NAT
Product Reorder Name: RX03013

LNP* VERTON* RX03013 is a compound based on PA 66 resin containing Long Glass Fiber, Proprietary Lubricant. Added features include: Internally Lubricated.

Property

TYPICAL PROPERTIES ⁽¹⁾			
MECHANICAL	Value	Unit	Standard
Tensile Stress, break, 5 mm/min	205	MPa	ISO 527
Tensile Strain, break, 5 mm/min	2.2	%	ISO 527
Tensile Modulus, 1 mm/min	12500	MPa	ISO 527
Flexural Stress, break, 2 mm/min	307	MPa	ISO 178
Flexural Strain, break, 2 mm/min	3.1	%	ISO 178
Flexural Modulus, 2 mm/min	10800	MPa	ISO 178
IMPACT	Value	Unit	Standard
Multiaxial Impact	5	J	ISO 6603
Izod Impact, unnotched 80*10*4 +23°C	70	kJ/m ²	ISO 180/1U
Izod Impact, notched 80*10*4 +23°C	28	kJ/m ²	ISO 180/1A
THERMAL	Value	Unit	Standard
HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm	265	°C	ISO 75/Bf
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	261	°C	ISO 75/Af
PHYSICAL	Value	Unit	Standard
Mold Shrinkage, flow, 24 hrs	0.4	%	ISO 294
Mold Shrinkage, xflow, 24 hrs	0.9	%	ISO 294
Density	1.44	g/cm ³	ISO 1183
Water Absorption, 23°C/24hrs	1.1	%	ISO 62-1

Source GMD, last updated:09/18/2008

Processing

Parameter	Value	Unit
Injection Molding		
Drying Temperature	80	°C
Drying Time	4	hrs
Maximum Moisture Content	0.15 - 0.25	%
Melt Temperature	290 - 305	°C
Front - Zone 3 Temperature	290 - 300	°C
Middle - Zone 2 Temperature	290 - 300	°C
Rear - Zone 1 Temperature	280 - 295	°C
Mold Temperature	95 - 110	°C
Back Pressure	0.2 - 0.3	MPa
Screw Speed	30 - 60	rpm

Source GMD, last updated:09/18/2008

THESE PROPERTY VALUES ARE NOT INTENDED FOR SPECIFICATION PURPOSES.

PLEASE CHECK WITH YOUR [\(LOCAL SALES OFFICE\)](#) FOR AVAILABILITY IN YOUR REGION

- (1) Typical values only. Variations within normal tolerances are possible for various colors. All values are measured after at least 48 hours storage at 23°C/50% relative humidity. All properties, except the melt volume and melt flow rates, are measured on injection molded samples. All samples tested under ISO test standards are prepared according to ISO 294.
- (2) Only typical data for selection purposes. Not to be used for part or tool design.
- (3) This rating is not intended to reflect hazards presented by this or any other material under actual fire conditions.
- (4) Internal measurements according to UL standards.

Disclaimer : All information, recommendation or advice given by SABIC Innovative Plastics, or any of its subsidiaries, affiliates or authorized representatives, whether written or oral, is given in good faith, to the best of its knowledge and based on current procedures in effect. Each user of the products shall convince himself, through all available sources (including finished product testing in its appropriate environment) of the suitability of the products supplied for its own particular purpose. Because actual use of the products by the user is beyond the control of SABIC Innovative Plastics Company, its subsidiaries and affiliates, such use is in the exclusive responsibility of the user. SABIC Innovative Plastics Company, its subsidiaries and affiliates cannot be held responsible respectively liable for any loss incurred through incorrect or faulty use of the products. Information, recommendations and/or advice are neither made to infringe on any patents, nor to grant a license under any patent or intellectual property right of SABIC Innovative Plastics Company or any of its subsidiaries or affiliated companies, nor to grant the right to file for any patent protection.

- * LNP is a trademark of the SABIC Innovative Plastics Company
- * Verton is a trademark of the SABIC Innovative Plastics Company

© 1997-2008 SABIC Innovative Plastics Company. All rights reserved